

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): An electrostatic developer, comprising:
toner-containing image-forming particles and an uncrosslinked, linear hydrocarbon based homopolymer wax,
wherein said wax has a total number of branches in each of one or more chains that is less than 0.5%, relative to a total number of carbons in said wax,
wherein said wax ~~is further characterized by having~~ has a set of endotherms as determined by differential scanning calorimetry (DSC) run at a maximum rate of 10°C per minute, said endotherms characterized by a primary endotherm and at least a secondary endotherm, said primary endotherm exhibiting a temperature range of between 70°C and 90°C and said secondary endotherm exhibiting a temperature range of between 95°C and 110°C;
[and]]
wherein said wax has a crystallinity of from ~~75% to 90%~~ 78 to 82% as determined by small angle X-ray diffraction analysis;
wherein said wax has a molecular weight polydispersity (Mw/Mn) in the range of 1.1-1.3, wherein the number average molecular weight, Mn, is in the range of 700-790 and the weight average molecular weight, Mw, is in the range of 890-1000; and
wherein said wax has the following branching:
0 - 0.20 methyl branches per 100 carbon atoms,
0 - 0.10 ethyl branches per 100 carbon atoms and
0 - 0.10 butyl branches per 100 carbon atoms.

Claims 2-4 (Canceled).

Claim 5 (Original): The electrostatic developer of claim 1, wherein said wax is further characterized by a particle size in the range of 1 to 10 μm .

Claim 6 (Original): The electrostatic developer of claim 1, wherein said wax is obtained by a process comprising:

in a reactor vessel, gasifying and subsequently liquifying coal to produce a wax residue in the reactor vessel, said reactor vessel containing sides with interior surfaces, wherein the wax residue forms on said surfaces;

milling said wax residue, substantially by a jet mill to accomplish micronizing of the wax.

Claim 7 (Canceled).

Claim 8 (Original): The electrostatic developer of claim 1, wherein said toner is a monocomponent toner.

Claim 9 (Original): The electrostatic developer of claim 1, wherein said toner is a dual component toner.

Claim 10 (Original): The electrostatic developer of claim 9, wherein said toner further comprises magnetic particles.

Claim 11 (Original): The electrostatic developer of claim 1, wherein said toner further comprises a binder resin.

Claim 12 (Original): The electrostatic developer of claim 1, wherein said toner further comprises a binder resin, and wherein said wax is present in an amount of 0.1-20 parts by weight per 100 parts of the binder resin.

Claim 13 (Original): The electrostatic developer of claim 1, said toner further comprises a binder resin, and wherein said wax is present in an amount of 0.1-7.0 parts by weight per 100 parts of binder resin.

Claim 14 (Original): The electrostatic developer of claim 1, said toner further comprises a binder resin, and wherein said wax is present in an amount of 1.0-6.0 parts by weight per 100 parts of binder resin.

Claim 15 (Original): The electrostatic developer of claim 1, further comprising one or more inorganic oxides selected from the group consisting of SiO_2 , Al_2O_3 , W_2O_3 , ZrO_2 , SeO , TiO_2 , ZnO , MgO , and mixtures thereof.

Claims 16-18 (Canceled).

Claim 19 (Original): A toner cartridge comprising a cartridge and the electrostatic developer according to claim 1.

Claim 20 (Original): In an electrophotographic apparatus, wherein the improvement comprises the use of a toner cartridge according to claim 19.